



# Product Data Sheet

## Transpoxy Tar 2.11

### Product description.

A polyamide cured coal tar epoxy coating with outstanding seawater resistance and flexibility. The product is eminently suitable for immersed areas, ballast tanks, void spaces and so on. It can be overcoated with various Transocean products.

### Physical properties.

Colour/Texture	Black and Redbrown/Semi-gloss
Volume Solids	64%
Specific gravity	1.48 gr/ml
VOC	345 gr/liter
Flashpoint	>25°C

	Dry film thickness per coat (μ)	Wet film thickness per coat (μ)	Theoretical spreading rate (m <sup>2</sup> /l)
Range	75 – 200	120 – 315	8.5 – 3.2
Recommended	125	200	5.1

### Application data.

<u>Mixing ratio</u>	By weight, base to hardener: 89 to 11. By volume, base to hardener: 82 to 18.
<u>Potlife</u>	5°C: 8 hours, 23°C: 4 hours, 30°C: 2 hours.
<u>Guiding data Airless spray</u>	Pressure at nozzle: 180 -250 bar. Nozzle size: 0.48 - 0.78 mm. Spray angle: 40 - 80 degrees. Volume of thinner: 0 - 5%.
<u>Guiding data Airspray</u>	Pressure. 4 - 6 bar. Nozzle size: 1.5 - 2.0 mm. Volume of thinner: 0 - 10%.
<u>Brush/Roller</u>	Suitable. Multicoats are required to achieve the specified dry film thickness. Volume of thinner: 0 - 5%.
<u>Thinner/Cleaner</u>	Transocean Epoxy Thinner 6.03.
<u>Conditions</u>	Humidity: below 85% RH. Temperature of the paint before application: min: 10°C, max: 30°C. Substrate temperature: min: 5°C, max: 35°C. The temperature of the substrate should be at least 3°C above the dew point of the air. Air temperatures and relative humidity must be measured in the vicinity of the substrate.

### Drying and recoating times.

Substrate temperature	Touch dry	Dry to handle	Full cure	Dry to recoat	
				Minimum	Maximum (1)
10 °C	6 hours	36 hours	10 days	24 hours	7 days
23 °C	3 hours	24 hours	7 days	12 hours	5 days
30 °C	2 hours	16 hours	4 days	8 hours	2 days

(1) The surface should be dry and free from contaminants prior to overcoating. When the maximum recoating time is exceeded it may be necessary to roughen the surface to ensure intercoat adhesion. When recoating with single pack products, maximum recoat interval is limited to 16-24 hours. When in doubt, consult your nearest Transocean office.

## Surface preparation.

Steel	Oil and grease should be removed by solvent cleaning according to SSPC-SP1. Remove weld spatter and smooth weld seams and sharp edges as applicable. Abrasive blasting: min. Sa2,5 – ISO 8501:1. Apply Transpoxy Tar PA 2.11 immediately after the steel has been blasted and the quality of preparation has been approved. Transpoxy Tar PA 2.11 may also be applied on Transpoxy primers such as Transozinc Epoxy Primer 1.55. Ensure that primed surfaces are dry and free from salts and other contaminants prior to overcoating.
Repair	Corroded areas should be power tool cleaned to ISO-St3 or blast cleaned to ISO-Sa2 or better. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.

## Recommended paint system.

A typical system for immersion conditions is shown below.

Transpoxy Tar 2.11 Black	1 x 125 µ dft.
Transpoxy Tar 2.11 Redbrown	1 x 125 µ dft.

## Worldwide availability

The product is part of the common Transocean product range but local availability is subject to confirmation. Although we strive to supply the same product through the world, slight modifications of the product in some cases may be necessary in order to comply with local conditions and/or national regulations. In such cases an alternative datasheet will be issued.

## Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapours and paint mist by wearing an air mask.

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

## Disclaimer

*The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product.*

*Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product.*

*We reserve the right to change the product without notice.*

Date of issue: February, 05.