

Product Data Sheet

Transogard Rustarrestor 4.16

Product description.

A modified alkyd based primer/coating pigmented with aluminium flakes. It has excellent wetting and penetration properties enabling application on substrates where good surface preparation is not possible. The product has the grain carriage approval by Newcastle Occupational Health Agency.

Physical properties.

Colour/Texture Volume Solids Specific gravity VOC	Silver/Semi-gloss 45% 1.0 gr/ml 436 gr/liter
	436 gr/liter
Flashpoint	>37°Č

	Dry film thickness per		Theoretical spreading
	coat (µ)	coat (µ)	rate (m ² /l)
Range	25 – 50	55 – 90	18.0 – 11.2
Recommended	30	70	15.0

Application data.

Guiding data Airless spray	Pressure at nozzle: 120 -180 bar. Nozzle size: 0.38 - 0.48 mm. Spray angle: 60 - 80 degrees. Volume of thinner: 0 - 3%.
Guiding data Air spray	Pressure: 3 - 5 bar. Nozzle size: 1.2 - 1.5 mm. Volume of thinner: 0 - 5%.
Brush/Roller	Suitable. Volume of thinner: 0 - 5%.
Thinner/Cleaner	Transocean Alkyd Thinner 6.00.
<u>Conditions</u>	Humidity: below 90% RH. Temperature of the paint before application: min: 5°C, max: 30°C. Substrate temperature: min: 5°C, max: 30°C. The temperature of the substrate should be at least 3°C above the dew point of the air. Air temperatures and relative humidity must be measured in the vicinity of the substrate.

Drying and recoating times.

Substrate	Touch dry	Hard dry	[Dry to recoat
temperature			Minimum	Maximum (1)
10 °C	8 hours	2 days	20 hours	Indefinite
23 °C	4 hour	1 day	16 hours	Indefinite
30 °C	3 hours	1 day	12 hours	Indefinite

(1) The surface should be dry and free from salts and other contaminants prior to overcoating. After prolonged exposure times it may be necessary to roughen the surface in order to ensure intercoat adhesion. When in doubt, consult your nearest Transocean office.

Surface preparation.

Coated substrates

The surface must be dry and free from salts and other contaminants. Remove salts and dirt by fresh water washing. Corroded areas should be power tool cleaned to ISO-St2 or blast cleaned to ISO-Sa2.

Recommended paint system.

Transogard Rustarrestor 4.16 can be applied over Transogard priming systems but may be used as the sole protective system on itself.

A typical system for cargo holds is shown below.

Transogard series	2 x 40 µ dft.
Transogard Rustarrestor 4.16	2 x 30 µ dft.

Worldwide availability

The product is part of the common Transocean product range but local availability is subject to confirmation. Although we strive to supply the same product through the world, slight modifications of the product in some cases may be necessary in order to comply with local conditions and/or national regulations. In such cases an alternative datasheet will be issued.

Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapours and paint mist by wearing an air mask.

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

Disclaimer

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product.

Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

Date of issue: February, 05.