



# Product Data Sheet

## Transurethane Elastic 3.42

### Product description.

A solventless, polyurethane coating for cargo holds. The product is high build and can be applied in a dry film thickness up to 500 micron in a single coat. Transurethane Elastic has good flexibility and impact resistance. It is approved for the carriage of grain by the Newcastle Occupational Health agency.

### Physical properties.

Colour/Texture	Sandyellow, RAL 1002/Glossy
Volume Solids	94%
Specific gravity	1.23 gr/ml
VOC	58 gr/liter
Flashpoint	>25°C

	Dry film thickness per coat (μ)	Wet film thickness per coat (μ)	Theoretical spreading rate (m <sup>2</sup> /l)
Range	200 – 500	215 – 530	4.7 – 1.9
Recommended	300	320	3.1

### Application data.

Mixing ratio By weight, base to hardener: 80 to 20.  
By volume, base to hardener: 78 to 22.

Potlife 10°C: 1 hour, 23°C: 45 minutes.

Guiding data Airless spray Heavy duty single feed airless. Compression 45 : 1, preferably 60 : 1.  
Pressure at nozzle: 250 -300 bar. Nozzle size: 0.53 - 0.66 mm.  
Spray angle: 40 - 80 degrees.  
Volume of thinner: 0 - 5%.

Brush/Roller Suitable for stripe coats and touch-up work only.  
Volume of thinner: 0 - 10%.

Thinner/Cleaner Transocean Polyurethane Thinner 6.04.

Conditions Humidity: below 85% RH.  
Temperature of the paint before application: min: 10°C, max: 30°C.  
Substrate temperature: min: 10°C, max: 35°C.  
The temperature of the substrate should be at least 3°C above the dew point of the air. Air temperatures and relative humidity must be measured in the vicinity of the substrate.

### Drying and recoating times.

Substrate temperature	Touch dry	Dry to handle	Full cure	Dry to recoat	
				Minimum	Maximum (1)
10 °C	16 hours	30 hours	10 days	24 hours	Indefinite
23 °C	12 hours	24 hours	7 days	16 hours	Indefinite
30 °C	8 hours	18 hours	5 days	12 hours	Indefinite

(1) The surface should be dry and free from contaminants prior to overcoating. The best intercoat adhesion is achieved when the subsequent coat is applied before the preceding coat is fully cured. After prolonged exposure times it may be necessary to roughen the surface to ensure intercoat adhesion. When in doubt, consult your nearest Transocean office.

## Surface preparation.

Steel	Oil and grease should be removed by solvent cleaning according to SSPC-SP1. Remove weld spatter and smooth weld seams and sharp edges as applicable. Abrasive blasting: min. Sa2,5 – ISO 8501:1. Apply Transurethane Elastic immediately after the steel has been blasted and the quality of preparation has been approved.
Repair	Corroded areas should be power tool cleaned to ISO-St3 or blast cleaned to ISO-Sa2 or better. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.

## Recommended paint system.

A typical system for cargo holds is shown below.

Transurethane Elastic 3.42                      1 x 300 µ dft.

Sharp edges, corners and weld seams must be stripe coated in order to achieve the specified dry film thickness.

## Worldwide availability

The product is part of the common Transocean product range but local availability is subject to confirmation. Although we strive to supply the same product through the world, slight modifications of the product in some cases may be necessary in order to comply with local conditions and/or national regulations. In such cases an alternative datasheet will be issued.

## Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately.

Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapours and paint mist by wearing an air mask.

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

## Disclaimer

*The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product.*

*Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product.*

*We reserve the right to change the product without notice.*

Date of issue: February, 05.